

REMARKS/ARGUMENTS


Favorable consideration of this application as presently amended and in light of the following discussion is respectfully requested.

Claims 1-18 are pending in the present application.

Accordingly, an action on the merits is earnestly solicited.

Respectfully submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.



Marvin J. Spivak
Attorney of Record
Registration No. 24,913

C. Irvin McClelland
Registration Number 21,124

Customer Number
22850

Tel: (703) 413-3000
Fax: (703) 413-2220
(OSMMN 08/03)

MJS:fb1

I:\USER\FBLAZ\NEW APPLICATION\243760.PRELIMINARY AMENDMENT.DOC

Table 1

	Measure- ment 1	Measure- ment 2	Measure- ment 3	Measure- ment 4	Measure- ment 5	Measure- ment 6	Measure- ment 7	Measure- ment 8
	Stacked thickness (μm)	Ratio of the apparent thickness to the initial thickness of the electrode	Amount of the electrolyte (g)	Initial expansion rate	Capacitance (F)	Resistance (m Ω)	Retention voltage (V)	Expansion rate after charging and discharging
Ex. 1	735	1.021	111	1.13	1650	2.21	2.444	1.15
Ex. 2	760	1.056	115	1.13	1550	2.41	2.451	1.15
Ex. 3	780	1.054	109	1.11	2210	3.22	2.391	1.48
Ex. 4	790	1.068	112	1.11	2180	3.31	2.401	1.51
Ex. 5	780	1.055	117	1.13	1570	2.33	2.460	1.16
Ex. 6	725	1.007	100	1.11	1619	3.53	2.055	1.12
Ex. 7	736	1.022	113	1.13	1650	2.18	0.507	1.55 1.115
Comp. Ex. 1	720	1.000	79	1.11	1412	5.42	0.221	1.11
Comp. Ex. 2	737	1.024	75	1.01	890	20.8	0.011	1.05